



®

TECHNICAL SPECIFICATION SHEET

HARRIS PRODUCTS GROUP
4501 QUALITY PLACE
MASON, OHIO 45040
 TEL. (513) 754-2000
 FAX, (513) 754-8778
www.harrisproductsgroup.com

...better ways to join metals

SILICON BRONZE WELDING WIRE

WARNING: PROTECT yourself and others. Read and understand this information.

FUMES AND GASES can be hazardous to your health.

ARC RAYS can injure eyes and burn skin.

ELECTRIC SHOCK can KILL.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDS), and your employer's safety practices.
- Keep your head out of fumes.
- Use enough ventilation, exhaust at the arc, or both, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- Do not touch live electrical parts.
- See American National Standard Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126; OSHA Safety and Health Standards, available from the U.S. Government Office, Washington, DC 20402

STATEMENT OF LIABILITY — DISCLAIMER

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. Harris Products Group and its affiliates shall have no liability in respect thereof.

NOMINAL COMPOSITION:

Manganese	1.5 % max.	Tin	1.0 % max.
Lead	0.02 % max.	Zinc	1.0 % max.
Copper	Remainder	Iron	0.50 % max
Silicon	2.8-4.0 %	Aluminum	0.01 % max.
Others	0.50 % max.		

PHYSICAL PROPERTIES:

Solidus	1780° f (971° C)	Liquidus	1880° f (1027° C)
Tensile Strength	50,000 psi. min.	Brinell Hardness	80-100 HB
		(500 kg load)	

All statements, information and data given are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

For technical support and product information, visit our web site at
www.harrisproductsgroup.com



...better ways to join metals

TECHNICAL SPECIFICATION SHEET

HARRIS PRODUCTS GROUP
4501 QUALITY PLACE
MASON, OHIO 45040
TEL. (513) 754-2000
FAX, (513) 754-8778
www.harrisproductsgroup.com

SILICON BRONZE WELDING WIRE

APPLICATION:

Used to weld base metals of steels and cast iron to copper, brass and bronze. May also be used to weld on galvanized steels.

RECOMMENDED WELDING PARAMETERS:

***GMAW (MIG) Parameters** (DC Reverse Polarity) Electrode Positive Spray transfer

<u>Wire Diameter</u>	<u>Amps</u>	<u>Volts</u>	<u>Argon (cfh)</u>	<u>Wire Feed ipm</u>
.030	130-150	21-23	25	460-500
.035	145-185	23-25	30	400-440
.045	195-215	26-28	30	280-310
1/16	260-280	27-30	40	150-210

***GTAW (Tig) Parameters** (DCSP) ² Electrode negative or ACHF

<u>Material</u>	<u>2% Thoriated ²</u>	<u>Filler Wire Size</u>	<u>Amps (DC)</u>	<u>Amps (AC)</u>	<u>Gas Cup</u>	<u>Argon(cfh)</u>
1/16"	1/16"	1/16"	70-150	70-150	3/8-1/2	15
3/32"-1/8"	3/32"	3/32"	150-200	140-230	7/16-1/2	15
3/16"- 1/2"	1/8"	3/32"-1/8"	230-400	225-320	7/16-1/2	20
1/2"-1"	3/16"	3/16"-1/4"	325-500	290-485	1/2	25

* All parameters are suggested as basic guidelines and will vary depending on joint design, number of passes and other factors.

SPECIFICATION COMPLIANCE: ANSI/AWS A 5.7 & ASME SFA-5.7 ERcCuSi-A

Harris Products Group	Fax	513-754-8778
4501 Quality Place	Tel.	513-754-2000
Mason, Ohio 45040		800-733-4533

Page 2 of 2

All statements, information and data given are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

For technical support and product information, visit our web site at www.harrisproductsgroup.com